



# آنالیز مونومر استایرن پتروشیمی پارس

(شیمی پل)

## خواص فیزیکی

استاندارد	شرایط	واحد	مقدار	نام
ASTM D5135	Maximum Value	%WT	0.04	alpha-Methylserotonin ((α-MS
ASTM D2119	Maximum Value	%WT	0.01	Benzaldehyde
ASTM D5135	Maximum Value, EB+Xylenes	%WT	0.06	C8 Content
ASTM D5135	Maximum Value, Aromatics+α-Ms	%WT	0.08	C9 Content
ASTM D1209	Maximum Value	APHA	10	Color
ASTM D5135	Maximum Value	%WT	0.05	Ethyl Benzene

ASTM D2340	Maximum Value	ppm	50	<b>Hydrogen Peroxide (H<sub>2</sub>O<sub>2</sub>)</b>
ASTM D4590	Maximum Value, As TBC	ppm	20	<b>Inhibitor</b>
ASTM D5135	Maximum Value	ppm	0.018	<b>Phenylacetylene</b>
ASTM D2121	Maximum Value	ppm	10	<b>Polymer</b>
ASTM D5135	Minimum Value	%WT	99.75	<b>Styrene Monomer</b>
ASTM D4929	Maximum Value, as Cl	ppm	2	<b>Total Chloride</b>
ASTM D5453	Maximum Value, As S	ppm	2	<b>Total Sulphur</b>

# Shimipole

