

# دیتاشیت HDPE EX³ (شیمی پل)

No.	Property	Unit	Test Method	Value
1 ▶	MFR(190 °C/5Kg)	g/10min	ISO 1133	0.45 ± 0.05
2 ▶	MFR(190 °C/21.6Kg)	g/10min	ISO 1133	12.0 ± 3.0
3 ▶	FRR21.6/5	---	---	26±4
4 ▶	Density	g/cm³	ISO 1183	0.945 ± 0.002
5 ▶	Notched Impact Strength	mJ/mm²	ISO179/1eA	> 12
6 ▶	Pipe Evaluation Hydrostatic Strength (80oc,4N/mm²)	Hours	(DIN 8074 & DIN 8075 & ISO 1167)	1000 min.

