

دیتاشیت ۰۲۰ LDPE (شیمی پل)

Specifications:

Property	Unit	Value	Test Method
MFI (190 °C/2.16 kg)	gr/10 min.	2	ASTM D 1238
Density	gr/ml	0.920	*TSTM 209 B
Softening point	°C	94	ASTM D 1525
Haze	%	15 max.	ASTM D 1003
Gloss @ 60	Gu	60 min.	ASTM D 523
Elongation @ break (MD)	%	330 min.	ASTM D 882
Elongation @ break (TD)	%	600 min.	ASTM D 882
Tensile @ break (MD)	kg/cm	160 min.	ASTM D 882
Dart impact	Gr	100 min.	ASTM D 1709

* TSTM = Toyo Soda Standard Test Method

The above data are typical laboratory average . They are intended to serve as guides only.

Shimipole

