

دیتاشیت ۲۴۲۰ LDPE (شیمی پل)

No.	Property	Value	Units	Test Method
1 ▶	Density	0.924	g/cm ³	ISO 1183
2 ▶	Melt flow rate (MFR)(190°C/2.16Kg)	1.9	g/10 min	ISO 1133
3 ▶	Tensile Modulus	260	MPa	ISO 527-1, -2
4 ▶	Tensile Stress at Yield	11	MPa	ISO 527-1, -2
5 ▶	Tensile Strength at Break MD/TD	26/18	MPa	ISO 527-1, -3
6 ▶	Tensile Strain at Break MD/TD	250/600	%	ISO 527-1, -3
7 ▶	Dart Drop Impact(50 blown film)	110	g	ASTM D 1709
8 ▶	Vicat softening temp(A50 (50 °C/h 10N))	94	°C	ISO 306
9 ▶	Haze (50)	<8.0	%	ASTM D 1003
10 ▶	Gloss (60 °,50)	>100		ASTM D 2457

Shimipole

