

دیتاشیت ۰۰۷۵ LDPE LH (شیمی پل)

Specifications:

Property	Unit	Value	Test Method
MFI (190°C/2. 16 kg)	gr/10min.	0.75	ASTM D 1238
Density	gr/ml	0.920	* TSTM 209 B
Vicat softening point	°C	95	ASTM D 1525
Elongation @ break (MD)	%	300 min.	ASTM D 882
Elongation @ break (TD)	%	450 min.	ASTM D 882
Tensile @ break (MD)	kg/cm ²	170 min.	ASTM D 882
HDT	°C	33	ASTM D 648
Dart impact	gr	120 min.	ASTM D 1709

* TSTM = Toyo Soda Standard Test Method

The above data are typical laboratory average . They are intended to serve as guides only.

Shimipole

