

LOTTE CHEMICAL

HOPELEX PC-1100U

Polycarbonate resin

General Information

Description

Hopelex PC-1100U is a medium viscosity, clear polycarbonate, which is suitable for outdoor injection applications. Hopelex PC-1100U have UV stabilized ingredients to prevent degradation of final PC products from lights.

Applications

Injection Products

Typical properties ¹								
					Test Method	d l	Typical value	Unit
Physical								
Melt Flow Index, 30	0 ℃,	1.2kg			ASTM D1238		10	g/10min
Specific Gravity					ASTM D792		1.20	
Mold Shrinkage					ASTM D955		0.5~0.7	%
Mechanical								
Tensile Strength, yi	eld,	50mm/min			ASTM D638		630	kgf/cm ²
Tensile Elongation,	, brea	ak, 50mm/m	in		ASTM D638		>100	%
Flexural Strength, y	∕ield,	10mm/min			ASTM D790		920	kgf/cm ²
Flexural Modulus,	10mn	n/min			ASTM D790		24,000	kgf/cm ²
IZOD Impact Streng	jth , r	notched, 23	℃, 1	/8"	ASTM D256		80	kg·cm/cm
	r	notched, 23	℃, 1	/4"	ASTM D256		-	kg· <mark>cm/cm</mark>
Thermal								
Heat Distortion Ten	np.	4.6kgf/cm ²			ASTM D648		143	${\mathbb C}$
		18.6kgf/ <mark>cm</mark> 2			ASTM D648		132	${\mathbb C}$
Vicat Softening Ter	np.	Rate B/50			ASTM D1525		150	${\mathbb C}$
Optical								
Light Transmittanc	е				ASTM D1003		89	%
Haze					ASTM D1003		< 0.8	%
Refractive Index					ASTM D542		1.585	

Į	0	tes	

ISO 9001, 14001, /TS 16949

¹ Typical properties: these are not to be construed as specifications.



www.lottechem.com



