

HANWHA

Ethylene Vinylacetate Copolymer

1533

Hot Melt Adhesive Grade

MELT INDEX 25
VA CONTENT 33.0

HANWHA EVA 1533 is manufactured by Dow autoclave high pressure process and designed for variety hot melt adhesive application. EVA 1533 is well known for its excellent adhesive property, mixing property with other raw materials and high quality assurance.

This product complies with U.S. FDA regulation 21 CFR 177.1350 (a)(1)

■ Outstanding Properties

Excellent Adhesive Property
Very Good Mixing Properties with other raw materials
Excellent low temperature physical property and flexibility
Good quality uniformity

■ Additives

Antioxidant, Anti-caking agent

■ Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	25
VA Content	wt%	HCC Method ⁽³⁾	33.0
Density	g/cm ³	ASTM D1505	0.955
Vicat Softening Point	°C	ASTM D1525	<30
Melting Point	°C	ASTM D3417	64
Tensile Strength at Break	kg/cm ²	ASTM D638	84
Elongation at Break	%	ASTM D638	820
Hardness	-	ASTM D2240	69

1. These are typical properties : not to be construed as specification.
2. The value for this property is dependent on part geometry and fabrication conditions.
3. Elemental Analyzer and FT-IR



Hanwha B/D, 1 Changgyo-dong, Chung-ku, Seoul, Korea. Tel : 82-2-729-1292 Fax : 82-2-729-3000

